MICCRO® PRODUCTS TECHNICAL INFORMATION DATA **MICCROPEEL**® STOP-OFF LACQUER



SUITABLE FOR USE IN THE FOLLOWING CYCLES:

HARD CHROME PLATING · BRIGHT CHROME · NICKEL

APPLICATION PROCEDURE

MICCROPEEL SHOULD BE STIRRED PRIOR TO USAGE

- Chemically and/or mechanically clean the area of the part to be masked. The area to be masked must be free of all dirt, grease, or other contaminates. NOTE: Cleaning is the most critical aspect of the masking procedure.
- 2. Apply MICCROPEEL[®] to the area to be masked by dipping, brushing or spraying. For reducing MICCROPEEL[®], use the MICCRO[®]REDUCER only.
- 3. Two or three coats are recommended depending upon the type of plating/chemical solution and/or length of processing time in solution. Allow at least a one-hour dry time between coats. A longer dry time between coats will improve the performance of the product. This factor is highly dependent on the severity of the plating cycle. Faster drying of MICCROPEEL[®] can be accomplished by force drying for 15 minutes in an oven. Temperatures must not exceed 140°F and times over 15 minutes. Dry time will vary according to relative humidity. NOTE: Make sure MICCROPEEL[®] has lost all solvent odor before force drying or applying additional coats. For maximum usage, we suggest an overnight dry before plating.
- 4. For extra long cycles, three coats are recommended. If area to be masked is highly polished, refer to the Masking Polished or Highly Smooth Surfaces" technical data page for improved adhesion.
- 5. MICCROPEEL[®] can be removed using MICCRO[®]REDUCER, MICCROSTRIP[®] A, and MICCRO SAFE-STRIP[®] C, MICCROPEEL[®] will not peel from the metal part.

CHARACTERISTICS

Color: Green • Wt./Gal: 7.9 lbs/gal • Coverage Rate: Approx. 280 ft.²(26m²) per gallon Viscosity: 200-250 cps • Flash Point: 24°F TCC • Dry film: 1.5 mil • VOC: 5.9 lbs/gal

Available in 1 gallon, 5 gallon and 55 gallon containers

