

MICCRO[®] PRODUCTS

TECHNICAL INFORMATION DATA

MICCROSHIELD[®]

STOP-OFF LACQUER



SUITABLE FOR USE IN THE FOLLOWING CYCLES:

ACID ETCHING • ANODIZING • ANY ACID CYCLE • BRONZE
ELECTRO POLISHING • ELECTROLESS NICKEL • GOLD ACID
GOLD NEUTRAL • INDIUM • LEAD • PALLADIUM • RHODIUM • SILVER

APPLICATION PROCEDURE

MICCROSHIELD SHOULD BE STIRRED PRIOR TO USAGE

1. Chemically and/or mechanically clean the area of the part to be masked. The area to be masked must be free of all dirt, grease, or other contaminants. NOTE: Cleaning is the most critical aspect of the masking procedure.
2. Apply MICCROSHIELD[®] to the area to be masked by dipping, brushing or spraying. Appropriate dilution of MICCROSHIELD[®] is required for spraying. For reducing MICCROSHIELD[®], use the MICCROSHIELD[®] REDUCER only.
3. Two or three coats are recommended depending upon the type of plating/chemical solution and/or length of processing time in solution. Allow at least a one-hour dry time between coats. A longer dry time between coats will improve the performance of the product. This factor is highly dependent on the severity of the plating cycle. Faster drying of MICCROSHIELD[®] can be accomplished by force drying for 15 minutes in an oven. Temperatures must not exceed 140°F and times over 15 minutes. Dry time will vary according to relative humidity. NOTE: Make sure MICCROSHIELD[®] has lost all solvent odor before force drying or applying additional coats. For maximum usage, we suggest an overnight dry before plating.
4. For extra long cycles, three coats are recommended. If area to be masked is polished, refer to the "Masking Polished or Highly Smooth Surfaces" technical data page.
5. MICCROSHIELD[®] can be removed using MICCROSHIELD[®] REDUCER, MICCROSTRIP[®] A, or MICCRO SAFE-STRIP[®] C.*

*Take off with a trichloroethylene vapor degreaser, although it is slower than the above methods.

CHARACTERISTICS

Color: Orange • **Wt./Gal:** 7.9 lbs/gal • **Coverage Rate:** Approximately 510 ft.²(47m²) per gallon

Viscosity: 45-50 sec (#2 Zahn) • **Flash Point:** 30°F TCC • **Dry film:** 1.1 mil • **VOC:** 5.81 lbs/gal

Available in 1 gallon, 5 gallon and 55 gallon containers

TOLBER[®]
PROVEN SOLUTIONS

220 WEST 5TH STREET, HOPE, ARKANSAS 71801

PH: (870) 777-3251 • FAX: (870) 777-8056 • www.TOLBER.com